

Jedamid 190G33L BK2091

Polyamide 66, Glass Filled, Black Color

General Information			
Product Description			
Jedamid 190G33L is fiberglass reinforced, polyamide 66.			
General			
Material Status:	• Commercial: Active		
Regional Availability:	• North America		
Filler/Reinforcement:	• Glass Fiber	33% filler by weight	
Additive:	• Internal Lubrication		
Recycled Content:	• No		
Features:	• Strength and Stiffness		
Appearance:	• Black Color		
Form:	• Pellet		
Processing Method:	• Injection Molding		
Properties			
Physical	Typical Value, DAM	Typical Value, Conditioned	Test Method
Density/Specific Gravity	1.39 g/cm ³		ASTM D792
Molding Shrinkage –			ASTM D955
Flow	0.3 %		
Across Flow	1.1 %		
Mechanical			
Tensile Modulus, psi	1,600,000	1,160,000	ASTM D638
Tensile Strength (Yield), psi	29,000	20,300	ASTM D638
Tensile Elongation (Break),%	3.5	5.0	
Flexural Strength (Yield), psi	42,500	29,000	ASTM D638
Flexural Modulus, psi	1,380,000	870,000	ASTM D790
Impact			
Notched Izod Impact Strength, ft-lb/in			ASTM D256
-40°F (-40°C)	1.85	1.85	
73°F (23°C)	2.20	2.73	
Thermal			
Deflection Temperature Under Load			
264 psi (1.8 MPa), Unannealed, 0.125 in	486 °F		ASTM D648
Peak Melting Temperature	505 °F		ASTM D3418



Jedamid 190G33L BK2091

Polyamide 66, Glass Filled, Black Color

Processing Information

Injection

Drying Temperature, °F	180
Drying Time, hr	2-4
Suggested Max Moisture, %	<0.20
Processing Melt Temperature,, °F	545 to 581
Melt Temperature, Optimum, °F	563
Mold Temperature, °F	158 to 248 °F
Mold Temperature, Optimum, °F	212 °F
Back pressure	As low as possible
Hold Pressure Time	3.0 sec/mm
Screw Tangential Speed	<472 in/min

Mechanical properties measured at 23°C (73°F)

Contact JEDA Polymers, LLC for MSDS, general guidelines and/or additional information about ventilation, handling, purging, drying, etc.

Jedamid® is a registered trademark of Jeda Polymers LLC

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since JEDA Polymers cannot anticipate all variations in actual end-use conditions JEDA Polymers makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body.