

Jedamid 190G13L NC010

Polyamide 66, Glass Filled, Natural Color

General Information			
Product Description			
Jedamid 190G13L is fiberglass reinforced, polyamide 66.			
General			
Material Status:	• Commercial: Active		
Regional Availability:	• North America		
Filler/Reinforcement:	• Glass Fiber	13% filler by weight	
Additive:	• Internal Lubrication		
Recycled Content:	• No		
Features:	• Strength and Stiffness		
Appearance:	• Natural Color		
Form:	• Pellet		
Processing Method:	• Injection Molding		
Properties			
Physical	Typical Value, DAM	Typical Value, Conditioned	Test Method
Density/Specific Gravity	1.23 g/cm ³		ASTM D792
Molding Shrinkage –			ASTM D955
Flow	0.7 %		
Across Flow	1.2 %		
Mechanical			
Tensile Modulus, psi	800,000	510,000	ASTM D638
Tensile Strength (Yield), psi	17,400	10,900	ASTM D638
Tensile Elongation (Break),%	3.0	13.0	
Flexural Strength (Yield), psi	23,900	13,500	ASTM D638
Flexural Modulus, psi	700,000	425,000	ASTM D790
Impact			
Notched Izod Impact Strength, ft-lb/in			ASTM D256
-40°F (-40°C)	0.80	0.54	
73°F (23°C)	0.80	0.73	
Thermal			
Deflection Temperature Under Load			
264 psi (1.8 MPa), Unannealed, 0.125 in	455 °F		ASTM D648
Peak Melting Temperature	505 °F		ASTM D3418



Jedamid 190G13L NC010

Polyamide 66, Glass Filled, Natural Color

Processing Information

Injection

Drying Temperature, °F	180
Drying Time, hr	2-4
Suggested Max Moisture, %	<0.20
Processing Melt Temperature, °F	545 to 581
Melt Temperature, Optimum, °F	563
Mold Temperature, °F	122 to 212 °F
Mold Temperature, Optimum, °F	176 °F
Back pressure	As low as possible
Hold Pressure Time	3.0 sec/mm
Screw Tangential Speed	<472 in/min

Mechanical properties measured at 23°C (73°F)

Contact JEDA Polymers, LLC for MSDS, general guidelines and/or additional information about ventilation, handling, purging, drying, etc.

Jedamid® is a registered trademark of Jeda Polymers LLC

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since JEDA Polymers cannot anticipate all variations in actual end-use conditions JEDA Polymers makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body.