

Jedamid ST150L NC010

Polyamide 66, Supertough, Natural Color

General Information

Product Description

Jedamid ST150L NC010 is an unreinforced, super toughened, polyamide 66.

General

Material Status:	• Commercial: Active			
Regional Availability:	• North America			
Filler/Reinforcement:	• None			
Additive:	• Impact Modifier			
Recycled Content:	• No			
Features:	• High Impact	• Good Melt Flow		
Uses:	• Automotive	• Agriculture	• Sporting Goods	• Fasteners
	• Zip Ties			
Appearance:	• Natural Color			
Form:	• Pellet			
Processing Method:	• Injection Molding			

Properties

Physical	Typical Value, DAM	Typical Value, Conditioned	Test Method
Density/Specific Gravity	1.08 g/cm ³		ASTM D792
Melt Mass-Flow Rate (MFR) 275 °C/2.16 kg	20.0 g/10 min		ASTM D1238
Molding Shrinkage –			ASTM D955
Flow	1.8 %		
Across Flow	1.4%		

Mechanical

Tensile Modulus, psi	290,000	140,000	ASTM D638
Tensile Strength, Yield, psi	7,300	6,300	ASTM D638
Tensile Elongation (Yield), %	6.0	35.0	ASTM D638
Tensile Elongation (Break), %	60.0	>100	ASTM D638
Flexural Strength (Yield), psi	9,900		ASTM D790
Flexural Modulus, psi	270,000	110,000	ASTM D790

Impact

Notched Izod Impact Strength, ft-lb/in			ASTM D256
-22°F (-30°C)	4.5	4.5	
73°F (23°C)	16.0	19.3	

Thermal

Deflection Temperature Under Load			
264 psi (1.8 MPa), Annealed, 0.125 in	160 °F		ASTM D648
Peak Melting Temperature	505 °F		ASTM D3418



Jedamid ST150L NC010

Polyamide 66, Supertough, Natural Color

Processing Information

Injection

Drying Temperature, °F	180
Drying Time, hr	2-4
Suggested Max Moisture, %	0.20
Processing Melt Temperature, °F	536 to 572
Melt Temperature, Optimum, °F	554
Mold Temperature, °F	122 to 212 °F
Mold Temperature, Optimum, °F	176 °F
Back pressure	As low as possible
Hold Pressure Time	4.0 sec/mm
Screw Tangential Speed	<710 in/min

Mechanical properties measured at 23°C (73°F)

Contact JEDA Polymers, LLC for MSDS, general guidelines and/or additional information about ventilation, handling, purging, drying, etc.

Jedamid® is a registered trademark of Jeda Polymers LLC

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since JEDA Polymers cannot anticipate all variations in actual end-use conditions JEDA Polymers makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body.